



zincblende and wurzite structures: hexagonal unit cells



WZ along (0001)



ZB along (111)

The different stacking (abab... and abcabc...) is referred to bilayers but also to the underlying different Bravais lattice structure (one of the sublattices), which is HEX in case of wurzite and FCC in case of zincblende